



# SILICONE SANITARY

## WATER-RESISTANT SILICONE SEALANT FOR ALL SANITARY APPLICATIONS



### PRODUCT DESCRIPTION

Permanently elastic, water resistant silicone sealant on an acetic acid base, specifically for sanitary sealings. Resistant to mould and very quick, shower can be used after 2 hours already\*.

### FIELD OF APPLICATION

For the sealing of seams, joints and crevices between wall, bath, shower cubicle, bathroom sink and kitchen counter in the sanitary areas like bathrooms, toilet and kitchens. Specifically for sealings in sanitary and ceramic applications, such as joints between wall and floor tiles, bath, shower cubicle, bathroom sink, kitchen counter, sink and tile walls. Also ideal for acrylic bathtubs, plastic shower bases and shower walls. Adheres to clear glass, ceramics, glazed tiles, enamel, metal, wood and various synthetics. Does not bond to bitumen, polyethylene, polypropylene and PTFE. Not suitable for aquariums; for this we recommend BISON Silicone Sealant Glass Transparent.

### PROPERTIES

- Mould resistant
- Very fast
- Permanently elastic
- UV and all-weather resistant
- (Sea)water resistant
- Resistant to temperatures between -50 °C and +120 °C
- Chemical resistant
- Easy to apply
- Excellent bonding without primer
- Colourfast
- Not paintable

### PREPARATION

**Working Conditions:** Only apply at temperatures between +5 °C and +40 °C.

**Surface Requirements:** The surface should be dry, clean and free of dust and grease. Synthetics should first be roughened and/or pre-treated with BISON Silicone Primer.

**Preliminary Surface Treatment:** For a good result, cover the joint's edges with masking tape. If necessary, prevent three-sided bonding by filling the joint with a foam backer rod or PE film.

**Tools:** Apply cartridge with a Power Pistol. Multi Tool to open the cartridge and tooling the sealant.

### APPLICATION

**Coverage:** Content suitable for approx. 8 to 15 m (depending on the diameter of the joint).

#### Directions for use:

Ensure a minimum joint width of 6 mm and a maximum of 20 mm. The joint depth depends on the joint width. Keep a joint depth of 6 mm up to a joint width of 12 mm. Beyond that, the joint depth should be half the joint width. Inject the sealant evenly into the joint and tool within 10 minutes with a putty knife, moistened with a soap solution. Remove the applied masking tape immediately after tooling. After approx. 15 minutes, a surface skin will form.

**Stains/residue:** Immediately remove stains with white spirit. The cured sealant can only be removed mechanically or with BISON silicone sealant residue remover.

**Points of attention:** Silicone hardens under the influence of humidity. Contact with humidity is therefore absolutely necessary during curing.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# SILICONE SANITARY

## WATER-RESISTANT SILICONE SEALANT FOR ALL SANITARY APPLICATIONS

### TECHNICAL SPECIFICATIONS

100% modulus:	0.3 MPa
Chemical base:	Silicone elastomer
Chemicals resistance:	Very Good
Cure rate:	2 mm/24h
Density approx.:	0,99 g/cm <sup>3</sup>
Elasticity:	Very good
Elongation of rupture:	500 %
Filling capacity:	Very good
Flash point:	K3 (>55°C)
Hardness (Shore A):	15
Max. bonding gap:	12,5
Maximum temperature resistance:	150 °C
Mildew resistance:	Very good
Minimum temperature resistance:	-30 °C
Moisture resistance:	Very good
Skinover time:	15 minutes
UV resistance:	Very good
Viscosity:	Pasty

### STORAGE CONDITIONS

At least 18 months after production.

Limited shelf life after opening.

Store in properly sealed packaging in a dry place at between +5 °C and +25 °C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.